



Desso Textile floor covering - Tiles

Libra Lines

Specification according to EN 1307

Type of manufacture	ISO 2424		Tufted 1/10 “					
Aspect	ISO 2424		Structured loop pile					
Dye method			Space dyed + solution dyed					
Dimension	EN ISO 24342	cm x cm	50 x 50 / 19,68” x 19,68” (20 tiles per box)					
Primary backing	ISO 2424		Polyester fleece					
Secondary backing	ISO 2424		Desso ProBase Polyver® - Polyscan®					
Pile fibre composition	ISO 2424		BCF Polyamide 6 and ECONYL® (ECONYL® is made from 100% regenerated content) **					
Total thickness	ISO 1765	mm	6.0	inch	0.2			
Effective pile thickness	ISO 1766	mm	2.5	inch	0.10			
Total mass	ISO 8543	g/m²	4100	oz/yd²	121.0			
Total pile mass	ISO 2424	g/m²	625	oz/yd²	18.4			
Effective pile mass	ISO 8543	g/m²	400	oz/yd²	11.8			
Pile density	ISO 8543	g/cm³	0.160	lb/in³	0.0058			
Number of tufts	ISO 1763	/dm²	1540	/yd²	128759			
Stroll test	ISO 6356	kV	≤ 2,0					
Vertical resistance	ISO 10965	Ohm	≤ 1 x 10⁹					
Horizontal resistance	ISO 10965	Ohm						
Use classification	EN 1307		33 Commercial - heavy use					
Luxury rating	EN 1307		LC 2					
Dimensional stability	EN 986	%	≤ 0,2					
Impact sound reduction ΔL _w	ISO 10140	dB	21					
Sound absorption	ISO 354	Freq. Hz	125	250	500	1000	2000	4000
		α _s	0.03	0.02	0.07	0.17	0.25	0.30
Noise reduction	ISO 354	α _w	0.15					
Thermal resistance	ISO 8302	m².K/W	0.032					
Flammability	EN 13501-1		Bfl - s1 (loose laid tested)					
Prodis - GUT	www.pro-dis.info		3A84F605					



** ECONYL® is a yarn made from 100% regenerated content. The total % of regenerated content varies per product and per colour. Whether a colour contains ECONYL® and the exact % thereof can be found on our website: www.desso.com.

Desso flooring products are to be installed in full accordance with Desso's installation instructions and recognised trade standards. An effective, regular cleaning and maintenance programme is vital for retaining a high appearance level. Desso flooring products should only be used as floorcoverings. Note: Desso reserves the right to amend this specification without giving prior notice. For the latest versions of the technical specifications, visit www.desso.com

EN-20171215